

Darley Buff



Technical Results

Description	Fine to medium grained Sandstone. Durable with good weathering qualities.	
Quarry location	Peak District, UK	
Geological Type	Carboniferous Sandstone	
Colour	Pale buff with occasional gold/brown variation.	
Density	2240kg/m ³	BSEN1936:2006
Compression Strength	97 MPa	BSEN1926:2006
Water Absorption	3.8%	BSEN13755:2008
Porosity	12.5%	BSEN1936:2006
Durability- Frost Resistance	9.72MPa	BSEN12371:2001
Flexural Strength (3-point)	6.6 MPa	BSEN13161:2008
Breaking Load at dowel hole	1810 N	BSEN1925:1999



Allgreen Group
46 Buckland Road
Pen Mill Trading Estate
Yeovil
Somerset
BA21 5EL

+44(0)1935 415560
sales@allgreengroup.co.uk

Please note stone is a natural product and these results are subject to variation.