



altro

the future is safer with altro



EN14041  
0120  
GB06/72664

Manufactured by:  
Altro Ltd, Works Road  
Letchworth Garden City  
SG6 1NW  
United Kingdom

## Altro Designer™ 25/D25

Altro Designer 25 / Altro D25 is a 2.5mm homogeneous, slip-resistant, resilient safety floor. Altro D25 includes aluminium-oxide throughout the thickness of the flooring complemented by silicon carbide and coloured quartz for life-time slip resistance and durability. [www.altro.com](http://www.altro.com)

Altro Designer 25 / Altro D25 es un pavimento de seguridad, antideslizante de 2,5 mm de espesor y homogéneo. Altro D25 incluye Óxido de Aluminio en todo su espesor, complementado con Carburo de Silicio y partículas de Cuarzo, para garantizar durabilidad y antiresbaladidad en toda la vida del producto. [www.altroscandess.es](http://www.altroscandess.es)

Altro Designer 25 / Altro D25 ist ein homogener 2,5 mm, rutschhemmender, elastischer Bodenbelag. Altro D25 beinhaltet Aluminiumoxid, Siliziumkarbid sowie farbige Quarze durch seine gesamte Belagsdicke für Rutsicherheit und Dauerhaftigkeit über die gesamte Lebensdauer des Belages. [www.altro.de](http://www.altro.de)

Colours Colores Farben	9		
Flooring Type Tipo de pavimento Belagsart		EN 13845/ EN 13553	Safety flooring Suelo de seguridad antideslizante Sicherheitsbodenbelag
Classification for use Areas de uso Einsatzbereiche		EN 685	34 & 43 34 y 43 34 & 43
Slip Resistance Resistencia al deslizamiento Rutschsicherheit		TRRL EN 13845 EN 13893 DIN 51130	≥ 36 ESf DS R10
Thickness Espesor Total Gesamtdicke		EN 428	2.5 mm
Wear Layer Capa de uso Nutzschicht		EN 429	2.5 mm
Flexibility Flexibilidad Flexibilität		EN 435	Pass Conforme bestanden
Weight Peso Flächengewicht		EN 430	3.1 kg/m <sup>2</sup>
Roll Dimensions Dimensiones del rollo Rollenabmessungen		EN 426	2.0m x 20.00m - 40m <sup>2</sup>
Light Fastness Resistencia a la luz Lichtechtheit		EN 20105-B02	≥6
Sound Insulation Aislamiento acústico Trittschal		ISO 140-8	7 dB
Wear Resistance Abrasión Verschleißverhalten		EN 13845	≤10% particles lost over 50000 Cycles ≤10% de las partículas perdidas en 50.000 ciclos ≤10% Partikel werden über 50000 Umdrehungen verloren
Indentation Punzonamiento Resteindruck		EN 433	≤ 0.10mm
Fire Performance Reacción al fuego Brandverhalten		EN 13501-1 EN ISO 9239-1 EN ISO 11925-2	Class Bfl-s1 ≥8kW/m <sup>2</sup> Pass Clase Bfl-s1 ≥8kW/m <sup>2</sup> Conforme Klasse Bfl-s1 ≥8kW/m <sup>2</sup> bestanden
Chemical Resistance Resistencia a los productos químicos Chemikalieneinwirkung		EN 423	Good Buena beständig
Castor Chair Abrasion Huellas de sillas de ruedas Stuhllöcherbeanspruchung		EN 425	Pass Conforme geeignet
Under floor heating Calefacción por el suelo Fußbodenheizung		EN 12667	Suitable Apto geeignet
Electrical Behaviours Características eléctricas Elektrisches Verhalten		EN 1815	≤ 2kV Antistatic ≤ 2kV Antiestáticas ≤ 2kV antistatisch
VOC Emissions Emisiones de VOC VOC Emissionen		pREN 15052 Section 01350 AgBB/DIBt	Low/Pass/Approved Baja/Conforme/aprobado gering/geeignet/zugelassen