

# ULTRASEAL® XP

## ACTIVE POLYMER WATERPROOFING MEMBRANE

### DESCRIPTION

ULTRASEAL® XP features XP technology, the latest innovation in active waterproofing. This advanced polymer technology provides exceptional performance in a wide range of ground contaminates, including high-saline conditions. Unlike passive membranes when used alone, the self-sealing ability of the active XP technology enables the ULTRASEAL® XP waterproofing membrane to seal minor cuts or damage to the membrane. And most importantly, it has been proven effective in both hydrostatic and non-hydrostatic conditions.

ULTRASEAL® XP works by forming a low permeability membrane upon contact with water. When hydrated, the unconfined membrane can swell many times its dry volume. When confined by backfill or concrete the swell is controlled, forming a dense, impervious waterproofing membrane. This swelling action can seal small concrete cracks caused by ground settlement and concrete shrinkage.

When concrete is poured against the XP geotextile side, ULTRASEAL® XP forms a strong mechanical bond. It contains zero VOCs, and can be installed in almost any weather condition directly to green concrete.

### APPLICATIONS

The ULTRASEAL® XP waterproofing system is intended to provide waterproofing protection for structural concrete surfaces under continuous or intermittent hydrostatic pressure; including high-saline and contaminated environments. Below ground applications include backfilled cast-in-place concrete and property line construction such as contiguous/secant piling and steel sheet piling. The membrane can be continued under the floor slab to provide a continuous, uniform waterproofing system. ULTRASEAL® XP applications include: Foundation walls, Earth-Covered Structures, Under Slab, and Tunnels. Please consult CETCO regarding specific ground contaminates.

### INSTALLATION

**General:** Install ULTRASEAL® XP Waterproofing System in strict accordance with the manufacturer's installation guidelines and details using accessory products, protection and drainage layers, and overburden as specified or required. Install ULTRASEAL® XP with the XP geotextile side directly in contact with the concrete to be waterproofed.

### SIZE AND PACKAGING

ULTRASEAL® XP is available in 1.22m x 7.6m rolls.

## TECHNICAL DATA

PROPERTY	TEST METHOD	TYPICAL VALUE
Hydrostatic Pressure Resistance	ASTM D5385 (Mod.)	70 m
Elongation at Break	EN ISO 527	25 %
Peel Adhesion to Concrete	ASTM D903 (Mod.)	1.7 kN/m
Puncture Resistance	EN ISO 12236	3.0 kN
Low Temperature Flexibility	ASTM D1970	Unaffected at -32°C
Tensile Strength	EN ISO 527	8.0 N/mm <sup>2</sup>

#### CETCO IN EUROPE:

Birkenhead Road, Wallasey, UK CH44 7UB, T: +44 (0) 151 606 5900 | F: +44 (0) 151 606 5932 | [www.cetco.co.uk](http://www.cetco.co.uk)  
 Szczytno 12-100, Korpele 13A - Strefa, Poland, T: +48 (89) 624 7301 | F: +48 (89) 624 7300 | [www.cetco.pl](http://www.cetco.pl)  
 Cheste (Valencia) 46380, Crta.CV-50, Spain, T: +34 902 820 200 | F: +34 902 820 300 | [www.cetco.es](http://www.cetco.es)

UPDATED: AUGUST 2013

IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. For the most up-to-date information, please contact CETCO sales team. CETCO accepts no responsibility for the results obtained through application of this product. CETCO reserves the right to update information without notice.