



Levelay HDT

HD Textured Floor Topping

USES

Levelay HDT provides a hardwearing, easily cleaned, low maintenance, attractive, textured floor surface which is chemically resistant, impervious and seamless. Levelay HDT floors are recommended for use in a wide range of industrial and commercial environments including laboratories, hospitals, food and beverage processing areas, pharmaceutical plants, electronics factories, kitchens, plant rooms, offices, production areas, workshops and warehousing areas.

DESCRIPTION

Levelay HDT is a flow applied epoxy resin flooring composition formulated from specially selected resins and high strength aggregates. Levelay HDT produces a finish of high strength and durability with excellent abrasion and impact resistance able to withstand aggressive operating conditions and comes with a textured surface for maximum anti-slip properties



BS EN 13813: 2002 / Synthetic Resin Screed Material

BS EN 13892-4:2002	Abrasion Resistance	AR 0.5
BS EN 13892-8:2002	Bond Strength	B 2.0
BS 8204:Part 1 2003	Impact Resistance	Cat. A

ADVANTAGES

Durable	good abrasion resistance, low maintenance costs
Hygienic	impervious, dustfree, easy to clean surface
Chemically resistant	good resistance to a wide range of industrial chemicals
Proven performance	long standing job references
Non-slip	textured surface provides excellent grip for pedestrian and vehicular traffic

PHYSICAL PROPERTIES

Compressive strength	86 N/mm ²
Tensile strength	14 N/mm ²
Flexural strength	44 N/mm ²
Shear strength	14.7 N/mm ²
Specific gravity	2.0
Viscosity of Levelay @ 23°C	30 Poises
Taber Abrasion Resistance:	
Levelay HD	690 microns thickness loss
35 N/mm² concrete control	1230 microns thickness loss

Slip Resistance Value – BS 7976-2 : 2002

4S Rubber Slider Wet	48
4S Rubber Slider Dry	63
TRL Rubber Wet	30
TRL Rubber Dry	97

CHEMICAL RESISTANCE

Levelay HDT is resistant to a wide range of chemicals. Specific data is available on request from the Technical Services Department.

COLOURS

Levelay HDT is available in a range of colours. For details refer to colour chart.

TEMPERATURE

Levelay HDT should not be applied at temperatures below 10° C and above 40° C

INSTRUCTIONS FOR USE

SURFACE PREPARATION

It is essential that the substrate surfaces are correctly prepared prior to application. New concrete or cementitious substrates should have been placed for at least 28 days, unless specially water reduced and give a protimeter reading of less than 75% RH. Conren WD Aquatect can be used for situations where the relative humidity is above 75% RH. All substrates should be sound and free from contamination. New or old floors should be prepared by vacuum blasting, grinding or light scabbling. Ensure that all substrates are free from rising damp. For the best results, all cracks, holes or damage to the subfloor should be repaired with Conren Patchfast epoxy resin mortar and be allowed to cure.

PRIMING – Please refer to Conren's Technical Services Department for further information regarding primers for the Levelay HDT system.



MIXING AND APPLICATION

Mechanical mixing is essential and a drill and paddle type mixer is recommended. Add the entire contents of the hardener container to the base container and mix for 3-4 mins, add the aggregate and mix for another 2 mins. The Levelay HDT should be poured onto the primed substrate and spread uniformly to the required thickness using a serrated steel trowel. The Levelay HDT should be rolled with a spiked nylon roller after application, to aid the release of any trapped air and to assist in leveling any slight trowel marks. The aggregate pack should then be broadcast across the surface of the Levelay HDT within 25-35 mins after application. Application of the aggregate should continue until a dry sandy surface is produced which is free from any Levelay bleeding through.

SEALING

Levelay HDT should be sealed with a coat of Conren Enamelcoat. The Levelay HDT should be at least 14 hours old and all excess, unbound aggregate removed from the surface before application. Proud aggregate can be removed with a scraper before sealing.

EXPANSION JOINTS

Expansion joints in the substrate should be maintained in the Levelay HDT topping.

COVERAGE & PACKSIZES

<u>Pack size - kg</u>	<u>Approx. Coverage per Aggregate Pack</u>
20kg	4 m ² + 12.5 kg @ 4mm
40kg	8 m ² + 25 kg @ 4mm

PRECAUTIONS

LEVELAY HDT should not be allowed to come into contact with skin and eyes or be swallowed. Avoid prolonged inhalation of solvent vapours. Epoxy resins and hardeners may act as skin sensitizers to some people. Gloves, goggles and a suitable barrier cream should therefore be used. Ensure adequate ventilation if working in enclosed areas suitable breathing apparatus must be used. Skin contamination with any of the products should be removed immediately with soap and water. In the event that mixed Aquasol comes into contact with the skin, it must be removed before it hardens with a good quality resin removing cream, followed by washing with soap and water. Do not use solvent. If accidental eye contamination occurs irrigate with copious quantities of clean water and seek medical advice. If ingestion of any of the materials takes place, seek medical attention immediately. Do not induce vomiting.

DISPOSAL

All tools and equipment should be cleaned using Conren Solvent Cleaner immediately after use. Spillage should be absorbed with sand or sawdust and disposed of in accordance with statutory regulations.

STORAGE

Shelf life at least 12 months if stored in original containers between 10° C and 25° C.

CONTRACTING SERVICE

Conren Limited offers a contracting service for the application of all Conren products. This facility is backed by a comprehensive technical and after sales service. We are able to contend with most problems in the field.

TECHNICAL SERVICE & QUALITY ASSURANCE

All information provided in this leaflet is based on results obtained from our own experience and test and is give in good faith. The user will be deemed to have satisfied himself independently of the suitability of Conren's products for his own particular purpose. We guarantee to replace, free of charge, any goods supplied by us which are proved to our satisfaction defective, but, as the application of these materials is necessarily beyond our control, we will not accept responsibility for any damage or loss arising wholly or in part from these materials. Except as herein provided, any express or implied condition, warranty, statement or representation, statutory or otherwise as to the quality of the goods is expressly excluded.

SPECIFICATION

Textured self-smoothing screeds to floors shall be Conren Levelay HDT.

All products to be applied in accordance with Conren's written instructions.

Conren Limited

Unit 1

The Bridge Business Centre

Ash Road South

Wrexham Industrial estate

Wrexham

LL13 9UG

Tel: +44 (0) 1978 661 991

Fax: + 44 (0) 1978 664 664

e-mail: info@conren.com

web: www.conren.com

SURFACING SOLUTIONS