





# CUPA 2

---

*Non-carbonated **slate** formed by tectonic compression.  
Dark grey slate with thin laminations and a **smooth surface**.*

 Riodolas mina, Carballeda de Valdeorras (Ourense) Spain.

 Operating since 1972.

 Sizes: 20x20 - 60x45 cm  
Thickness: 3.5 - 5 - 6 mm



## Formats



Rectangular Square Half Moon Waben Schuppen Fishschuppen 90° Sawn

## Selections



## Technical specifications

ABSORPTION	CARBONATE NON CARBONATED	MOR CHARACTERISTIC	SO <sub>2</sub> EXPOSURE TEST	THERMAL CYCLE TEST	FREEZE THAW TEST
0,14% Code: W1 (< 0,4%)	0,27% Fullfil (< 2%)	Longitudinal 54 MPA	S1	T1	Fullfil < 0,4%

## International certifications



European Standard: EN 12326 | French Specifications: NF 228-02/01/01 | Belgian Specifications: ATG/H652 | British Standard: BS 680 Part 2