

CUPA 3

DESCRIPTION Non-carbonated slate formed by tectonic compression. Blue black slate with non rusting metallic particles and thin laminations.


ORIGIN Quarry Solaña de Forcadas. San Pedro de Trones (León) Spain. Operating since 1892.

PRODUCTION 15.000 t/year

SIZES (CM) 25x15 - 50x45

THICKNESS (MM) 3.5 - 5 - 7.65

FORMATS



SELECTIONS

R EXCELLENCE

H

NATURAL

HEAVY

3



TECHNICAL SPECIFICATIONS

European Standard: EN 12326

British Standard: BS 680 PART 2

French Specifications: NF 228-02/01/01

Belgian Specifications: ATG H571

WATER ABSORPTION	0,25% Code: W1 (< 0,4%)
CONTENTS OF CARBONATE NON CARBONATED	0,47% Fullfil (< 2%)
MOR CHARACTERISTIC	Longitudinal 55 MPA
SO ₂ EXPOSURE TEST	S1
THERMAL CYCLE TEST	T1
FREEZE THAW TEST	Fullfil < 0,4%

INTERNATIONAL CERTIFICATIONS

