






CUPA 50

Non-carbonated slate formed by tectonic compression. Deep grey slate with thin laminations and very uniform smooth surface.



 San Vicente Quarry, Villamartín de Valdeorras (Ourense) Spain.

 Operating since 1999.

 Sizes: 20x20 - 60x45
Thickness: 3,7-5-6,5-7,5 mm



Formats



Selections



Technical specifications

ABSORPTION	CARBONATE NON CARBONATED	MOR CHARACTERISTIC	SO ₂ EXPOSURE TEST	THERMAL CYCLE TEST	FREEZE THAW TEST
0,13% Code : W1 (< 0,6%)	0,50% Complies (< 2%)	Longitudinal 58.9 MPA Transversal 60.5 MPA	S1	T1	Fulfill < 0,6%

International certifications

