

## TECHNICAL SHEET 10.02.35-eng DECORATIVE RENDER FINISHES



# JUBIZOL TREND FINISH S 1.5 in 2.0

Siloxane acrylic smooth render for vivid colours

### 1. Description, Application

JUBIZOL TREND FINISH S 1.5 in 2.0 are pasty thin-coat render finishes for vivid colours only for JUBIZOL EPS External Thermal Insulation Composite (ETIC) systems, based on polymeric binders, with a characteristically textured surface. These renders provide decorative protection to façade wall surfaces of all types of buildings including multi-storey buildings with short eaves. They adhere well to all coarse construction surfaces: conventional fine lime-cement and cement plasters, smoothed concrete surfaces, as well as fibre-cement and gypsum-cardboards, chipboards, and similar.

The selected ratio between fine and rough fillers and a combination of modern thickening agents, and substances for water retention **assure these render finishes low toughness** enabling easier application and expansion as well as **significantly longer processing time of the applied render finishes**. High content of siloxane additives, which are added to UNIXIL G renders, ensures **high water repellence and high resistance to smoke, ultraviolet rays and other atmospheric factors** and, consequently, **solid resistance in any climate conditions**. They are also characterised by **high strength** and due to **relatively high water-vapour permeability**, which is not typical for acrylic render finishes, they may also be applied as the top-coat of ETIC systems made on mineral wool. Surfaces coated with these render finishes have an assured **long-term resistance to contamination with wall algae and mould**. Therefore, **it is not necessary to add any biocidal substances prior to application**.

### 2. Packaging

25kg plastic tubs.

### 3. Colour Shades

- NOT in white (colour shade 1001)
- colour shades of the JUB PAINTS AND RENDERS colour chart (on JUMIX tinting stations at points of sale) : colours whose last digit of a 4-digit code is 0 and 1.
- colour shades of the JUB FAVOURITE FEELINGS colour chart (on JUMIX tinting stations at points of sale): colours whose final letter of a 4-digit code is A and B as well as some with C.
- 10 colour shades of the JUB colour chart PAINTS and RENDERS + 44 colours of the JUB FAVOURITE FEELINGS colour chart modified with COOL technology (available on order - tinting is performed only in the JUB factory).

We offer a selection of ten colour shades out of the JUB colour chart PAINTS and RENDERS whose lightness value Y is below 25 ( $Y < 25$ ) as UNIXIL COOL render finish. They incorporate special IR-reflecting pigments (IR = infrared light). These cause an essentially lower warming of sunlit façade surfaces than render finishes tinted with conventional pigments do. There is no limitation in application of UNIXIL COOL render finishes regarding the lightness value Y (usually limited to  $Y > 25$ ).

Ten colours (JUB PAINTS AND RENDERS) which we offer with COOL technology (shown colours are for information only – for a genuine view of the colours please refer to the most recent JUB colour chart PAINTS and RENDERS):



- under certain conditions, there is the possibility to produce colour shades on customer's request.



#### 4. Technical Data

		JUBIZOL TREND FINISH S 1.5	JUBIZOL TREND FINISH S 2.0
Density (kg/dm <sup>3</sup> )		~1.80	~1.80
Drying time – touch dry T = +20 °C, relative air humidity = 65 % (hours)		~6	~6
Water-vapour permeability EN ISO 7783-2	μ coefficient (-)	<200	<200
	Sd value (m)	<0.30 (for d = 1.5 mm) class V2 (medium water-vapour permeability)	<0.40 (for d = 2.0 mm) class V2 (medium water-vapour permeability)
Water absorption w <sub>24</sub> EN 1062-3 (kg/m <sup>2</sup> h <sup>0.5</sup> )		<0.04 class W3 (low water absorption)	<0.04 class W3 (low water absorption)
Adhesion to standard lime-cement plaster (1: 1: 6) EN 24624 (MPa)		>0.30	>0.30

Main ingredients: acrylate binder, coarse and fine calcite and aluminosilicate fillers, cellulose agents, titanium dioxide, siloxane additives, water.

#### 5. Surface Preparation

The surface should be slightly rough (ideal is the roughness of a conventionally smoothed fine render of 1.0 mm granulation), solid (compressive strength of at least 1.5 MPa – CS II by EN 998-1), dry and clean, without weakly bound particles, dust, easy water-soluble salts, oil stains and other filth. Any smaller uneven parts – protrusions and indentations – hinder the smoothing of the applied render finish; therefore it is important to attend to the preparation of the surface.

Prior to the application of a decorative render finish, the newly applied base-coats have to dry at least 7 to 10 days for each cm of its thickness. Decorative render finishes are applied to new concrete surfaces only a month after concreting (stated drying times of the surface are valid in normal conditions: T = +20 °C, relative air humidity = 65 %). Coatings, slurries and other decorative coats have to be removed from old solid plasters/renderers. After the surface had been cleaned, it should be thoroughly dusted by washing and, if necessary, mended and levelled. Washing the surface with a high-pressure water blaster (hot water or steam) is especially recommended in the case of fibre-cement boards and all concrete surfaces since it removes panel oil from new surfaces and soot, moss, lichen, remains of old coatings and similar from old ones.

Suitable primers for individual types of surfaces are stated in the table below:

Surface	Primer	Consumption (depends on absorption and coarseness of surface)
Fine lime-cement renders, EWI base-coats	UNIGRUND (a shade closest to the render finish colour)	120 – 200 g/m <sup>2</sup>
	Water-diluted ACRYLCOLOR (a shade closest to the render finish colour; ACRYLCOLOR : water = 1 : 1)	90 – 100 ml/m <sup>2</sup>



	Water-diluted AKRIL EMULSION (AKRIL EMULSION : water = 1 : 1)	90 – 100 ml/m <sup>2</sup>
Smooth, low-absorbing surfaces (concrete, fibre-cement boards) and excessively absorbing surfaces (gypsum-cardboards, chipboards)	UNIGRUND (a shade closest to the render finish colour)	120 – 200 g/m <sup>2</sup>
	VEZAKRILPRIMER	~300 ml/m <sup>2</sup>

Primers are applied with a painting or masonry brush, while ACRYLCOLOR and AKRIL EMULSION can also be applied with a long-fibre fur or textile paint roller or by spraying. The application of a render finish should start only when a primer is dried through. In normal conditions (T = +20 °C, relative air humidity = 65 %), the drying time for UNIGRUND is at least 12 hours, for VEZAKRILPRIMER at least 24 hours, while for ACRYLCOLOR and AKRIL EMLSION from 4 to 6 hours.

## 6. Preparation of Render Finish for Application

Prior to application, stir the render finish with an electric mixer, and, if necessary (only exceptionally), dilute it with water (maximum 1 dl per container). The colour shade must be checked; then, equalize the render finish in order to remove even the slightest or imperceptible differences in colour shade between individual buckets. Stir the content of four buckets well in a large container of appropriate size. When a quarter of the so prepared compound is used, the content of the next bucket is poured into the container and mixed properly with the rest of the render finish, etc. Equalisation of white renders, which belong to the same production batch or to the same production date and which have not been diluted, is not necessary.

Reworking the render finish during application (adding tinting agents, diluting, and similar) is not allowed.

## 7. Render Finish Application

The render finish is applied manually - using a stainless steel smoothing trowel – or by spraying – in the thickness slightly above the diameter of the thickest grain. When the render finish is applied by spraying, follow the instructions of the producer of the mechanical equipment. Immediately after the application, smooth the surface with a solid plastic finishing trowel. Perform the smoothing by circular strokes until an evenly grained structure is achieved. Move the grains in the applied render finish coat as little as possible during smoothing to avoid material bulges in front of the trowel. Reasons for their occurrence are mostly a too thick render layer or an uneven or a not well enough prepared substrate. At the end – a few minutes after smoothing, push protruding lumps into the surface by smoothing the surface slightly using a clean stainless steel smoothing trowel.

Perform the application as fast as possible, without any interruptions from one corner of the wall to the other. When applying the render finish onto wall surfaces higher than one floor, it must be applied simultaneously to all floors: in such cases, always begin the application at the top floor, while performing a phase-delayed “step shift” in lower floors. Larger wall surfaces should be divided into smaller sections by using adequately wide decorative grooves, mortar trims, and other decorations, frames or in any other way. In this manner we avoid potential problems caused by continuous application of the render finish as well as non-aesthetic appearance due to a potentially uneven surface. Joints between planes in inner or outer corners can be made easier by preparing a few cm wide, finely smoothed stripes, which also give a pleasant decorative appearance to processed surfaces. Decorative smoothed stripes, grooves, mortar trims, frames, and similar are usually made prior to the application of the decorative render finish. They are protected by suitable wall paints, while paying attention not to apply coatings encroaching onto surfaces prepared for the application of the render finish.

The application of a decorative render finish is possible only in suitable weather or microclimate conditions: the temperature of the air and the wall surface should be between +5°C and +35°C and the relative air humidity should be below 80 %. Protect façade surfaces from sun, wind and rainfall with protective scaffold nettings; however, do not conduct any work in rain, fog or strong wind (≥30 km/h) despite such protection.

In normal conditions (T = +20°C, relative air humidity = 65 %), resistance of freshly processed surfaces to damage caused by precipitation (washing away of the application) is achieved in 24 hours at the latest.

Approximate or average consumption:

JUBIZOL TREND FINISH S 1.5	~2,5 kg/m <sup>2</sup>
JUBIZOL TREND FINISH S 2.0	~3,0 kg/m <sup>2</sup>



## 8. Safety at Work, Waste Management, Tool Cleaning

Protection of eyes with protective glasses or with safety mask is necessary only when applying the decorative render finish by spraying. In all other cases, the use of personal protection means and the application of special measures for safe use are not necessary. Apart from general instructions and regulations for construction and painting works and instructions stated in the safety sheet, please consider also the following warnings:

- H412 Harmful to aquatic life with long lasting effects
- P101 If medical advice is needed, have product container or label at hand.
- P102 Keep out of reach of children.
- P103 Read label before use.
- P273 Avoid release to the environment.
- P501 Dispose of contents/container in line with local/regional/national/international regulations.

Containing: 2-Octyl-2H-isothiazol-3-one (OIT), mix of 5-chloro-2-methyl-2h-isothiazol-3-one and 2-methyl-2h-isothiazol-3-one (3:1), 1,2-Benzisothiazol-3(2H)-one. May cause allergic reaction.

Protection of coating from algae and mould is enabled with the content of: Terbutryne, zinc pyrithione, 2-Octyl-2H-isothiazol-3-one (OIT).

Keep unused render finish in a well-sealed packaging for potential repairs. Deposit hardened remains and wastes onto the dumping grounds of construction waste (waste classification number: 17 09 03\*). Liquid remains shall be deposited onto the dumping ground for waste paints and resins containing organic solvents or other dangerous substances (waste classification number: 08 01 11\*).

Thoroughly clean the tools with water immediately after use. Dried stains cannot be removed. The product or tool cleaning water must not reach ground water, sewage system or surface water. Waste water shall be collected and used during the following works. Remains of unused waste water shall be handed to an authorised dangerous waste deposit.

Cleaned packaging can be recycled.

## 9. Maintenance and Restoration of Painted Surfaces

Façade surfaces processed with JUBIZOL TREND FINISH S 1.5, or 2.0 render finishes do not require any special maintenance. The non-adhering dust and other non-adhering filth can be swept, hoovered or washed away with a water blaster. Adhering dust and more obstinate stains can be removed by light rubbing with a soft brush soaked into a solution of usual universal household preparations and washed away by clean water.

However, where filth and stains cannot be removed applying the methods described above, renovation painting is recommended. In such cases, apply two coats of the micro-reinforced façade paint REVITALCOLOR AG or REVITALCOLOR SILICONE onto a prior coat of an appropriate primer.

## 10. Storage, Transportation Conditions and Durability

Storage and transportation at temperatures between +5°C and +25°C, protected from direct sunlight, out of the reach of children, MUST NOT FREEZE!


Shelf life when stored in originally sealed and undamaged packaging: at least 12 months.

## 11. Quality Control

The product's quality characteristics are determined with the internal manufacturing specifications as well as with the Slovenian, European and other standards. We constantly monitor the declared or set quality level in our own labs, at the ZAG Construction Institute in Ljubljana and occasionally also at other independent institutions at home and abroad. The quality level is also ensured by the ISO 9001 system for total quality management and control, which has been implemented at JUB for many years. During the manufacturing process, we strictly comply with the Slovenian and European standards for protection of the environment and for ensuring security and health at work, which is confirmed by the ISO 14001 and OHSAS 18001 certificates.

The adequacy of JUBIZOL TREND FINISH S 1.5 and 2.0 as top-coats of JUBIZOL ETIC systems has been approved with the European Technical Approval (ETA). In accordance with the ETAG 004/2000 guidelines, the testing was performed at the ZAG Construction Institute in Ljubljana.



	
JUB d.o.o. Dol pri Ljubljani 28 SI – 1262 Dol pri Ljubljani <b>14</b> Product Type Identification no.: 10.02.35 Decl.of Performance no.: 001/14-JUBIZOL TREND FINISH S	
<b>SIST EN 15824</b> External render finish based on organic binders	
Vapour permeability	V2
Water absorption	W3
Adhesion	≥0,3 MPa
Thermal conductivity $\lambda_{10,dry}$	0,83 W/mK, P = 50% (tab. vrednost EN 1745)
Reaction to fire	A2

## 12. Other Information

The technical instructions in this brochure are given based on our experiences and are given as a guideline for achieving optimal results. We cannot take any responsibility for the damage, caused by incorrect selection of a product, incorrect use or unprofessional work.

The colour shade may differ from the print in the colour chart or from the approved sample. However, the total colour difference  $\Delta E_{2000}$  for shades from the JUB's PAINTS AND RENDERS and FAVOURITE FEELINGS colour chart – it is determined in accordance with the ISO 7724/1-3 and with a mathematical model CIE DE2000 – does not exceed 2.5. In order to check the colour shade, a dry application of render finish on a test surface is compared to a standard of the concerned shade, which is stored in the TRC JUB d.o.o. A colour shade of a render finish made on the basis of other samplers and colour charts is the best possible approach for JUB's product bases and tinting agents. Therefore, in such cases the total colour difference from the desired shade may be even higher than the value guaranteed above. A difference in colour shade, which is the result of unsuitable working conditions, of a product preparation technique, which differs from the one in this technical sheet, of failure to follow the equalisation rules, of the application of the product onto an unsuitably prepared, overly or not enough absorbing surface, more or less coarse surface, on a wet or not dried enough surface, cannot be subject of complaint.

If applied within External Wall Insulation systems, render finishes shall have brightness (Y) over 25. Darker render finishes and render finishes of intensive colour shades, which can be achieved only with organic pigments, are less stable under heavy conditions of use, somewhat less resistant to being washed out by precipitation and tend to chalk more. Complaints about changes, which might thus occur on exposed façade surfaces, especially in the form of faster bleaching, will not be accepted. Therefore, one should consult JUB's experts for each case individually regarding conditions for the application of such renders and the maintenance of processed surfaces. The list of such susceptible colour shades is available at stores where JUMIX tinting stations are located as well as in our sales and technical information departments.

This technical sheet supplements and replaces all preceding editions. We reserve the right to change and supplement data in the future.

Denomination and date of publishing: **TRC-107/14-pek**, 27.03.2015

JUB kemična industrija d.o.o.,  
 Dol pri Ljubljani 28, 1262 Dol pri Ljubljani, SLOVENIA  
 Phone: (01) 588 41 00 Main Reception Desk,  
 (01) 588 42 17 Sales Department,  
 (01) 588 42 18 or 080/15 56 Technical Support  
 Fax: (01) 588 42 50 Sales department  
 e-mail: jub.info@jub.si  
 Web page: [www.jub.eu](http://www.jub.eu)

