

# WALL TILE GROUT

## Cement-Based Wall Tile Grout



- ◇ Fine Texture
- ◇ Low Abrasion
- ◇ 1-3mm Joints
- ◇ Easy Mix
- ◇ Interior Use
- ◇ BS EN 13888 CG1

A fine textured water resistant cement-based wall tile grout for use in up to 3mm wide joints in ceramic, stone, porcelain and mosaics on rigid substrates. The fine texture of the grout is designed to prevent scratching of tile surfaces during the grouting process.

Conforms to BS EN 13888 CG1

Pot Life @ 20°C	Set Time @ 20°C	Joint Width	Specific Gravity	Coverage
Approx. 2 hours	Approx. 24 hours	1-3mm	2.0	1kg will fill joints of approximately 4m <sup>2</sup> of 150mm x 150mm x 6mm tiles with 2mm wide joints or 1.5m <sup>2</sup> of 20mm x 20mm x 4mm mosaics with 2mm spacing <b>Coverage Calculation:</b> $\frac{(\text{Width} + \text{Length}) \times \text{Joint Width} \times \text{Tile Depth} \times \text{Specific Gravity}}{\text{Width} \times \text{Length}} = \text{kg/m}^2$ e.g. for a 150mm x 150mm tile, 6mm thick with a 3mm joint width: $\frac{(150 + 150) \times 3 \times 6 \times 2}{150 \times 150} = 0.48\text{kg/m}^2$

Internal	External	Walls	Floors	Flexible	Total Immersion	Domestic Showers	Commercial/Power Showers	Fine Texture	Mould Resistant	Hygiene/Sterile Areas
Y	N	Y	N	N	N	Y	N	Y	N	N



# WALL TILE GROUT

## General Preparation

Prior to grouting the adhesive should be dry and the grout joints clean, dry and free of adhesive residues. Porous tiles should be sealed before grouting with a preparatory sealer. If in doubt trial an inconspicuous area to check for staining before grouting commences.

## Mixing

In to a clean pail add 1 part of cold water and gradually introduce approximately 3 parts of grout powder. Stir continuously until a smooth lump free blend is achieved.

No further water should be added after the initial mixing.

## Application

Using a soft rubber grout float apply the material with diagonal sweeping movements to the grout joints, taking care to compress the grout into the full depth of the joints. Work in manageable areas and clean off any residues when the grout has begun to firm up in the joints but not before it sets on the tile face. Cleaning with a damp, but not overly wet clean foam rubber sponge will provide the best results. Changing the cleaning water as it becomes contaminated with grout residues will also aid cleaning. When the grout has set, any remaining grout film can be polished off the surface with a clean damp cloth.

**N.B.** Do not over wet the grout as this will result in a weakened grout joint and can also cause efflorescence, a white soluble salt, to form on the surface of the finished grout joint.

**Norcross Wall Tile Grout** is a cement-based grout and as with all cement containing products the surface may be susceptible to the formation of efflorescence/soluble salts. These salts may be removed once the grout has fully dried and cured by frequent washing with clean water or a suitable efflorescence remover.

**Important Information:** Norcross Wall Tile Grout is water resistant but not impervious to the passage of water. In installations where the background needs to be protected against water ingress the use of **Norcross Wet Seal Tanking Membrane** should be considered. Where an impervious grout joint is required **Norcross Super Epoxy Grout** should be used.

## Colours Available:

White  
Crème

## Storage

Store in dry internal conditions away from direct sunlight between 5-25°C. The product has a 12 month shelf life from date of manufacture.

## Technical Advice

For advice on tile installation products call **Norcross Technical Helpline** on **01782 524 140**

