



# ALLBASE

## Surface Preparation:

Pre-sand the surface using a drum sander fitted with Pallmann ABRASIVE GRADE 36 to 60 grit. Then fill the joints with PALL-X KITT mixed with fine sanding dust. Sand with Pallmann ABRASIVE GRADE 100 grit (using a drum sander). The last final sanding part is recommended with the Pallmann Abrasive grade or Multihole-Pad 120 grit using a rotary sanding machine. After the final sanding, the floor must be clean, dry and free from sanding dust and contamination.

## Application:

1. Before use, bring the containers to the recommended room temperature and shake well, then decant the contents into a clean bucket.
2. Apply two full and uniform coats of Pallmann ALLBASE with the LSM APPLICATION ROLLER (for solvent-based lacquers). Begin at the edge, applying first across the grain and then with the grain. Second coat must be applied after approx. 45 minutes.
3. The primed surface can be over-coated with solvent-based lacquers, after a drying time of approx. 60 minutes. For PALL-X 96, PALL-X 98 and PALL-X EXTREME, a drying time of 2 – 3 hours is required.
4. Clean tools after use with clean tools after use with a suitable thinner.

## Consumption:

2 roller-applied coats is recommended:

Recommended quantity per coat: approx. 60 – 100 ml/m<sup>2</sup>

Coverage per litre: approx. 10 – 16 m<sup>2</sup>

## Important Notes:

- Shelf life minimum 12 months in original packaging when stored in relatively cool conditions. Tightly reseal opened packaging and use as quickly as possible
- Optimum conditions are 18 – 25 °C, relative humidity > 35 % and < 65 %. Low temperatures and high humidity lengthen, whilst high temperatures and low humidity shorten the drying time.
- Do not use a spark forming stirring equipment, e.g. electrical drill etc.
- When using other lacquer systems, please obtain technical advice. ALLBASE is approved only for use with PALL-X 96, PALL-X 98 and PALL-X EXTREME.
- ALLBASE must not be sanded and must be overcoated after no more than 24 hours.
- The following standards and publications are applicable and especially recommended: DIN 18356 "Working with parquet", DIN 18367 "Working with wood-blocks".

## Protection of the Workplace and the Environment:

High solvent content. Hazard symbol F: "highly flammable". Solvent vapour can form explosive mixtures with air. Ventilate well during and after use. Do not smoke and avoid open lights and flames. Prevent sparks and, therefore, disconnect all electrical equipment, switches, etc. During application, use barrier cream and protective gloves. Refer especially to: the hazard / safety notes on the container label.

## Disposal:

Where possible, collect product residues and re-use. Do not allow into drains, water courses or landfill. Empty, drip-free plastic or metal containers are recyclable [Interseroh]. Containers with liquid residues, as well as collected, liquid product residues, are Special Waste. Containers with dried residues are Construction Waste.

The above information is based on our experience and careful investigations. The variety of associated materials and different construction and working conditions cannot be individually checked or influenced by us. The quality of your work depends, therefore, on your own professional judgement and product usage. If in doubt, conduct a small test or obtain technical advice. Observe the installation recommendations of the covering manufacturer.

The publication of this Product Data Sheet invalidates all previous product information. The respective updated version of this datasheet can be found on our homepage under [www.pallmann.net](http://www.pallmann.net)

