

Property	Value	According to
Reaction to Fire, Euroclass	A1 _L	EN 14303:2009 (EN 13501-1)

Thermal Properties

Thermal Resistance		
Property	Value	According to
Thermal Conductivity (declared) in 50 °C, λ_{50}	0.041 W/mK	EN 14303:2009+A1:2013 (EN ISO 8497)
Thermal Conductivity (declared) in 100 °C, λ_{100}	0.047 W/mK	EN 14303:2009+A1:2013 (EN ISO 8497)
Thermal Conductivity (declared) in 200 °C, λ_{200}	0.063 W/mK	EN 14303:2009+A1:2013 (EN ISO 8497)
Thermal Conductivity (declared) in 250 °C, λ_{250}	0.073 W/mK	EN 14303:2009+A1:2013 (EN ISO 8497)
Thermal Conductivity (declared) in 300 °C, λ_{300}	0.085 W/mK	EN 14303:2009+A1:2013 (EN ISO 8497)
Thermal Conductivity (declared) in 400 °C, λ_{400}	0.110 W/mK	EN 14303:2009+A1:2013 (EN ISO 8497)
Dimensions and Tolerances	T8/T9	EN 14303:2009+A1:2013

Moisture Properties

Water Permeability		
Property	Value	According to
Water Absorption, Short Term WS, W_p	$\leq 1 \text{ kg/m}^2$	EN 14303:2009+A1:2013 (EN 13472)

Rate of Release of Corrosive Substances

Trace Quantities of Water Soluble Ions and the pH Value		
Property	Value	According to
Chloride Ions, Cl ⁻	< 10 ppm	EN 14303:2009+A1:2013 (EN 13468)

Durability

Durability of Reaction to Fire Against Ageing/Degradation

The fire performance of mineral wool does not deteriorate with time. The Euroclass classification of product is related to the organic content, which cannot increase with time.

Durability of Reaction to Fire Against High Temperature

The fire performance of mineral wool does not deteriorate with high temperature. The Euroclass classification of the product is related to the organic content, which remains constant or decreases with high temperature.

Durability of Thermal Resistance Against Ageing/Degradation

Thermal conductivity of mineral wool products does not change with time, experience has shown the fibre structure to be stable and the porosity contains no other gases than atmospheric air.

Durability of Thermal Resistance Against High Temperature

Thermal conductivity of mineral wool products does not change with time, experience has shown the fibre structure to be stable and the porosity contains no other gases than atmospheric air.

Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, www.paroc.com

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: international use (general information).