



- The flooring shall be Polysafe Arena PUR, as manufactured by Polyflor Ltd. of Manchester, England.
- The flooring shall be flexible PVC sheet flooring in 2.0mm thickness, with the following construction: circa 0.7mm clear PVC wear layer with aluminium oxide granules incorporated throughout the full thickness - to impart enhanced slip resistance, a fibreglass reinforced integral print layer and circa 1.30mm of PVC backing.
- The flooring shall feature a high quality, cross-linked polyurethane reinforcement to provide superior cleaning benefits, life cycle maintenance savings and optimum appearance retention.



- The flooring material shall fully conform with the European Norm for safety flooring - EN 13845.
- In respect of flamespread, the flooring shall be certified as Class Bfl-S1 according to EN 13501-1. The flooring shall have been fully tested to ASTM E648 by an independent test house and have a Class 1 rating, making it suitable for use in institutional, commercial and public buildings.
- The flooring must have been fully tested by an independent test house to the RRL Pendulum Test (4S Rubber/Slider 96) and have results of  $\geq 36$  in the wet, with a surface roughness of  $R_z \geq 20\mu\text{m}$ , making it suitable for use in areas where enhanced slip resistance is required.
- The product must have been fully tested for abrasion resistance to the Frick Taber test EN 660: part 2 and be in abrasion group T, as defined in EN 649 and meet the EN 13845 50,000 cycles test.
- This product does not accumulate static charges above 2kV and is classified as 'antistatic' when tested to EN 1815. For specialist applications where there is a requirement to dissipate the electrostatic charge, see the Polyflor ESD product ranges.
- The flooring shall possess a valid Agrément certificate when laid in accordance with the instructions of Polyflor, with coved skirtings and welded joints.
- The flooring must be available in 2.0 metre width, to minimise the number of joints.
- The flooring is suitable for Use Area Classification 23/34/43, as defined in EN ISO 10874 (EN 685).
- In respect of light fastness, the flooring shall have been fully tested to ISO 105-B02 Method 3 and obtain  $\geq 6$ .



- The flooring will achieve BRE Global Environmental Generic A+ rating in major use areas such as education and healthcare.
- Generic EN 15804 Environmental Product Declaration (EPD) available on request.
- The manufacturer should provide a facility to take back and recycle waste vinyl flooring material through the Recofloor scheme.
- The flooring shall be tested to and pass key independent, international standards for low VOC emissions.



- The manufacturer of the floorcovering must be in possession of a valid quality systems certificate, showing compliance with BS EN ISO 9001.
- The manufacturer of the floorcovering must be in possession of a valid environmental certificate showing compliance with ISO 14001.



- A moisture test must be carried out, to ensure that the subfloor has dried out to a level consistent with the application of vinyl flooring. The test should be carried out using a hygrometer, in accordance with the instructions in BS 8203. The result should not exceed 75%RH, once equilibrium has been achieved.
- The adhesive used must be approved by Polyflor, to ensure full product compatibility.
- Products must be fully conditioned to the environment in which they are to be installed, as outlined by Polyflor.
- Installation must be carried out in accordance with BS 8203 and the instructions of Polyflor.
- All joints must be welded.



- Polysafe Arena PUR is ideal for use in busy front of house public areas which are normally dry but where there is a risk that water spillage can occur, making slip resistance an important consideration. Typical areas include corridors and circulation areas, receptions, hospital wards, classrooms, shops and cafes as well as social housing applications and normal back of house safety areas. This includes washrooms, bar serveries and changing rooms. For continually wet areas please refer to our Polysafe Hydro or Hydro Evolve ranges.
- The slip resistance across all Polysafe products is assured throughout the guaranteed life of the product, with strict adherence to HSE Guidelines. As with all Polysafe products, Polysafe Arena PUR should not have a polish applied.



- Polysafe safety flooring ranges are compatible for use with the most commonly used alco-based hand gels and are suitable for steam cleaning on a periodic basis. For clarification and for information regarding handling and installation, adhesives, maintenance, applications and chemical resistance, consult Polyflor Customer Technical Services on +44 (0)161 767 1912, or email tech@polyflor.com. For best results, flooring must be reverse laid.
- At the date of issue the data presented is correct. However, Polyflor Ltd. reserves the right to make changes which do not adversely affect performance or quality.

POLYFLOR LTD. PO BOX 3 RADCLIFFE NEW ROAD WHITEFIELD MANCHESTER M45 7NR UK  
 UK SALES DIRECT: +44 (0)161 767 1122 UK SAMPLE REQUESTS: +44 (0)161 767 2551  
 EXPORT SALES DIRECT: +44 (0)161 767 1913 TECHNICAL SUPPORT: +44 (0)161 767 1912  
 RECEPTION: +44 (0)161 767 1111 UK FAX: +44 (0)161 767 1128  
 EXPORT FAX: +44 (0)161 767 1166  
 E-MAIL: INFO@POLYFLOR.COM WWW.POLYFLOR.COM

*James Hatfield*  
 FLOORING



2011



# POLYFLOR POLYSAFE™ ARENA PUR



## PRODUCT SPECIFICATION



Refer to the BRE Green Guide for more details  
 (www.thegreenguide.org.uk)



In collaboration with the European Resilient Flooring Manufacturers' Institute (ERFMI), Polyflor Ltd supports sustainable construction via Environmental Product Declarations (EPDs).

