

Ronafix for Renders



Admixture for weatherproof renders and waterproof / tanking renders



FEATURES

- waterproof (mix design E)
- weatherproof (mix design A)
- frostproof
- high compressive strength
- high tensile strength
- high flexural strength
- pre-packed for increased confidence
- can be laid from 6mm

Description

Ronafix is a BBA Approved single part modified styrene butadiene liquid additive for cement mortars which enhances physical and chemical properties, allows mortars to be placed in thin section, provides waterproofing and resistance to frost and promotes adhesion to building surfaces.

Mortars containing Ronafix are used for a wide range of applications where thin high strength high performance mortars are required. Typical minimum application depth is 6mm.

There are 2 mix designs when using Ronafix as a waterproof render. Ronafix Mix Design A is used for weatherproofing and Ronafix Mix Design E is used for tanking.

Physical Properties (Mix A)

Compressive Strength

1 day	38N/mm ²
3 days	45N/mm ²
7 days	56N/mm ²
28 days	70N/mm ²

Tensile Strength

7 days	5.0N/mm ²
28 days	7.1N/mm ²

Flexural Strength

7 days	12.9N/mm ²
28 days	16.2N/mm ²

Physical Properties (Mix E)

Compressive Strength

1 day	22N/mm ²
3 days	34N/mm ²

Ronafix for Renders

Admixture for weatherproof renders and waterproof / tanking renders

Physical Properties (Mix E) (continued)	7 days	42N/mm²
	28 days	53N/mm²
	Tensile Strength	
	7 days	5.7N/mm²
	28 days	8.4N/mm²
	Flexural Strength	
	7 days	15.8N/mm²
	28 days	19.1N/mm²
	Compression tests:	100mm cubes
	Flexural tests:	100 x 25mm x 25mm prisms
	Tensile tests:	dumbell specimens
	Test Authority:	British Precast Concrete Federation CMC Laboratories W & C French Ltd Ronacrete Laboratories

Laboratory Results: Results shown are in N/mm². Maximum laboratory strengths are achieved by casting and curing cubes in ideal working conditions; site strengths will be lower.

Mix Design Ronafix Mix A Weatherproof Renders	By weight	
	Cement	50kg
	Medium sharp sand	125kg
	Ronafix	9 litres
	Water	9 litres (approximately)
Mix Design Ronafix Mix E Tanking	By weight	
	Cement	50kg
	Medium sharp sand	125kg
	Ronafix	14 litres
	Water	4 litres (approximately)

Instructions for Use

Preparation

The substrate on which the Ronafix render is being placed must be structurally sound and stable and suitable to receive and support a strong render. Surfaces should ideally be prepared by recyclical shot blasting, water/grit blasting or similar means to expose the aggregate and provide a mechanical key. All grease, oil, dirt and deleterious material must be removed by vacuuming.

Ronafix for Renders

Admixture for weatherproof renders and waterproof / tanking renders

Instructions for Use (continued)

Damping

The prepared surface must be thoroughly dampened with clean water. All surplus and standing water must be removed before the primer is applied.

Priming

Brush apply a primer of 1:1 Ronafix : cement to the damp surface immediately before applying the Ronafix modified mortar. Mix the primer thoroughly and apply evenly over the surface ensuring total and uniform coverage. Only prime an area which can be covered by the render within the working time of the primer.

Note that the primer must not be allowed to dry. If it dries it must be thoroughly cross hatch scratched and reapplied.

Mixing

Mix the Ronafix modified mortar and apply in layers to achieve the required thickness, reform the original profile of the concrete and cover reinforcing steel. Layer thickness will vary according to the nature of the substrate, the shape and size of area being repaired and mixing and application technique.

Ronafix modified mortars can be mixed by hand or machine. Machine mixing will more easily provide a mortar with even dispersion of mix components and a lower water/cement ratio. The use of a forced action mixer (eg. Creteangle or drill and paddle) will provide optimum performance; free fall mixers cause the mortar to ball up with a resultant reduction in performance and must not be used.

Placing

As soon as the material is mixed render it onto the wet/tacky primer, using conventional plastering techniques ensuring total contact with the substrate and ensuring the render does not slump or slide away from the surface.

If applying two or more coats of Ronafix render apply each layer after the previous layer has firmed up sufficiently to support its weight without slumping or pulling away. Keying and priming between layers is necessary to ensure total adhesion through the render.

When applying waterproof renders using mix design E it is necessary to apply not less than two coats, each not less than 6mm thick. Joints must be staggered and the render should be carried down on to the floor to form a coving. The joint between a waterproof render and a waterproof screed must also be staggered.

Curing

As soon as possible after finishing the surface cure the surface with Monocure 50. Alternatively use tight fitting polythene to prevent rapid moisture loss and surface cracking and crazing.

BBA Certification

Ronafix has been tested by the British Board of Agreement for its waterproofing properties and Certificate No. 86/1651 has been issued for the application of external renders.



Ronafix for Renders



Admixture for weatherproof renders and waterproof / tanking renders

Site Attendance

Site Attendance

When on site Ronacrete representatives are able, if asked, to give a general indication of the correct method of installing a Ronacrete product. It is important to bear in mind that Ronacrete Ltd is a manufacturer and not an application contractor and it is therefore the responsibility of the contractor and his employer to ensure he is aware of and implements the correct practices and procedures to ensure the correct installation of the product and that liability for its correct installation lies with the contractor and not with Ronacrete Ltd.

Ronacrete Ltd, Flex Meadow, Harlow Essex, CM19 5TD, UK 13 0836-CPR-13/F042 0836-CPR-13/F043
BS EN 934-2 BS EN 934-3 Concrete Admixture Masonry Mortar Admixture
Product: Ronafix Chloride ion content: $\leq 0.1\%$ Alkali Content: $\leq 0.5\%$ Dangerous Substances: None

The information detailed in this leaflet is liable to modification from time to time in the light of experience and of normal product application, and before using, customers are advised to check with Ronacrete Ltd, quoting the reference number, that they possess the latest issue. Any person or company using the product without first making further enquiries as to the suitability of the product for the intended use does so at his own risk, and Ronacrete Ltd can accept no responsibility for the performance of the product, or for any loss or damage arising out of such use.

Waterproofing and Tanking

Ronacrete