

TECHNICAL DATA SHEET

Product: Alreflex Ultratherm
Issue Number: 007
Issue Date: Jan 2013

Product Information

Description

Alreflex Ultratherm is a rigid, polyisocyanurate (PIR) foam board; laminated with a single layer of Alreflex 1L1 polythene bubble sheet, faced with low-emissive aluminium foil protected by a thin NC coating. Alreflex Ultratherm incorporates unique, lapped joints to prevent rain ingress.

Application

For use in walls as a partial-fill cavity wall insulation and cavity rain barrier (*BBA Certificate No. 93/2861*).

Appearance & Packaging

Supplied in boards, stock sizes (*other sizes available on request*):

Board Size : 0.45m x 1.2m

Physical Properties

Thickness : 20mm – 140mm
Density : 30 kg/m³ (BS EN 13163)
Compressive Strength : 120 kPa (@ 10% compression) (BS EN 826)

Surface Flame Spread of bubble/foil : Class 0 (BS 476-7)
Surface Flame Spread of PIR (25-90mm): Class 1 (BS 476-7)
Water Vapour Resistance of bubble/foil : 125MN · s/g (BBA Certificate No. 93/2861)
Water Vapour Resistance of PIR : 100MN · s/g (BBA Certificate No. 93/2861)

If you require any further technical information please contact our Technical Department on 01582 544255.

Thermal Performance

Foil Emissivity	: 0.05	(BBA Certificate No. 93/2861)
Resistance of (min) 20mm residual cavity	: $0.71\text{m}^2 \cdot \text{K/W}$	(BBA Certificate No. 93/2861)
Resistance of bubble/foil	: $0.08\text{m}^2 \cdot \text{K/W}$	(BBA Certificate No. 93/2861)
Thermal Conductivity of PIR (λ)	: $0.022\text{ W/m} \cdot \text{K}$	(BS EN 13163)

Environmental Data

BRE Green Guide Rating : A+

Global Warming Potential : < 5

Ozone Depletion Potential : 0