

PYROSWISS® Climaplus

Fire resistant safety glass for interior and exterior application

CLASSIFICATION

E = Integrity


Ability to withstand fire exposure without transmission of fire to the non-fire side as a result of the passage of flames or hot gases, thereby causing ignition of the non-fire exposed surface or materials adjacent.

PRODUCT FEATURES

Fire resistant toughened safety glass with low emission and/or solar control properties

Inner pane
Toughened glass or Float glass

Spacer



TECHNICAL SPECIFICATIONS

Fire resistance (EN 13501-2)

Reaction to fire (EN 13501-1)

Maximum Glass Size

Thickness tolerance

Length tolerance

CE certificate No. of conformity

Heat Soak Test

Hazardous material contained

E 30

B-s1, d0

Variable, subject to glass make-up, framing material or glazed element type.

Consult with your Vetrotech representative.

± 1 mm

± 2 mm

0336-CPD-5064D/ID No.* (you can obtain a DoP** from your national sales office) - AoC-level 1

available upon request

None

Nominal thickness

Fire Risk

Outer pane

Spacer

Inner pane

Impact resistance (EN 12600) (outside/inside)

Weight

Sound reduction R_w (EN 140-3)

Light transmission (EN 410)

Light reflection ρ_L (exterior/interior)

U value, W/m^2K (EN 673)

g value

Energy transmission τ_E

Energy reflection ρ_E (exterior/interior)

24 mm

one side

6 mm PYROSWISS®

12 mm with Air filling

6 mm toughened glass

1 (C) 1/1 (C) 2 classification

31 kg/m^2

33 dB***

78%

12%/12%

1,6

0,57

52%

24%/25%

* ID No. = Identification number for the relevant manufacturing site

** Declaration of Performances

*** Reference Value

PYROSWISS® Climaplus

Fire resistant safety glass for interior and exterior application

CLASSIFICATION

E = Integrity


Ability to withstand fire exposure without transmission of fire to the non-fire side as a result of the passage of flames or hot gases, thereby causing ignition of the non-fire exposed surface or materials adjacent.

PRODUCT FEATURES

Fire resistant toughened safety glass with low emission and/or solar control properties

Inner pane
Toughened glass or Float glass

Spacer



TECHNICAL SPECIFICATIONS

Fire resistance (EN 13501-2)

Reaction to fire (EN 13501-1)

Maximum Glass Size

Thickness tolerance

Length tolerance

CE certificate No. of conformity

Heat Soak Test

Hazardous material contained

E 30

B-s1, d0

Variable, subject to glass make-up, framing material or glazed element type.
Consult with your Vetrotech representative.

± 1 mm

± 2 mm

0336-CPD-5064D/ID No.* (you can obtain a DoP** from your national sales office) - AoC-level 1

available upon request

None

Nominal thickness

Fire Risk

Outer pane

Spacer

Inner pane

Impact resistance (EN 12600) (outside/inside)

Weight

Sound reduction R_w (EN 140-3)

Light transmission (EN 410)

Light reflection ρ_L (exterior/interior)

U value, W/m^2K (EN 673)

g value

Energy transmission τE

Energy reflection ρE (exterior/interior)

26 mm

both sides

6 mm PYROSWISS®

14 mm with Argon gas filling

6 mm PYROSWISS®

1 (C) 1/1 (C) 1 classification

31 kg/m^2

33 dB***

78%

12%/12%

1,1

0,57

52%

24%/25%

* ID No. = Identification number for the relevant manufacturing site

** Declaration of Performances

*** Reference Value