

WOODPECKER

NATURALLY INSPIRED FLOORING

TECHNICAL DATA & APPLICATION

PVA ADHESIVE

A premium, flooring grade PVA adhesive ideal for bonding tongue and groove boards. It's easy to apply, solvent-free and fully cured within four hours of application. The approximate coverage per bottle is 5m² depending on the method of application and width of floor planks.



TECHNICAL DATA

MATERIAL.....	PVA dispersion
CURING SYSTEM	Physical drying
CONSISTENCY	Liquid
COLOUR	White
VISCOSITY (mPAS).....	Approx 13,000 mPas
OPEN TIME AT 18-20°C AND 60% RH	Approx 10 minutes
SET TO LOADBEARING	Minimum 24 hours
PH VALUE.....	Approx 3
TOTAL SOLIDS CONTENT	Approx 100%
APPLICATION RATE.....	200 linear metres of 3mm bead per litre

APPLICATION:

Apply with a brush or suitable applicator for applying a bead of adhesive. Joint surfaces should be sound, dry, clean of dust and free from contamination. Apply evenly to one surface only. Assemble the bond whilst the adhesive is still wet and apply pressure by clamping or weighting to maintain a tight joint until the adhesive has dried, at least 24 hours depending on temperature and absorberency of the surfaces. The temperature should be maintained above 10°C during application.

Tools should be cleaned with water while the adhesive is still wet.

STORAGE:

Store between 5°C and 30°C. Protect from frost.

Shelf life is 12 months when unopened and stored appropriately.

SPECIFICATION DISCLAIMER

This technical data sheet was written by Woodpecker Flooring and at the time of writing and publication, all information was specified correctly. The company reserves the right to change specification without notice. Customers should confirm that the product is still available with the specification shown.

Woodpecker House, 29 Pant Glas Industrial Estate, Bedwas, Caerphilly CF83 8DR

T: 02920 888 223 F: 02920 881 694 info@woodpeckerflooring.co.uk

WWW.WOODPECKERFLOORING.CO.UK